

Subject
B3
62. (amended) An apparatus for impregnating a continuous fiber material, comprising a heater for heating a fibrous reinforcing material to a first temperature, a means for applying a tension to the fibrous reinforcing material, and a container containing a molten resin composition, said container having an inlet and an outlet for the heated fibrous reinforcing material in which the heated reinforcing material is contacted with the molten resin composition; wherein the container includes therein a shearing mechanism for the fibrous reinforcing material.

B4
70. (twice amended) An apparatus according to claim 62, further including molding equipment for forming impregnated fibrous reinforcing material exiting the container into an article of a desired shape.

B5
72. (amended) An apparatus for preparing a reinforced matrix resin composition, comprising a heater for heating a fibrous reinforcing material, a molten resin composition that is located so as to first contact the heated fibrous reinforcing material while the heated fibrous reinforcing material is at a first temperature, and a compressing unit for pressing the heated fibrous reinforcing material together with the resin composition; wherein the first temperature is above the temperature of the resin composition.

B6
74. (amended) An apparatus according to claim 72, wherein said first temperature is from about 75°F to about 500°F above the temperature of the resin composition.

B7
78. (amended) An apparatus for preparing a reinforced matrix resin composition, comprising a heater for heating a fibrous reinforcing material to a first temperature and a container of a liquid, crystallizable resin composition having an inlet and an outlet for the heated fibrous reinforcing material; wherein the heater is at a temperature and location so that the first temperature, as measured at the point where the heated fibrous reinforcing material is brought into contact with the resin